




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : B03D 1/02	A1	(11) International Publication Number: WO 00/15346 (43) International Publication Date: 23 March 2000 (23.03.00)
<p>(21) International Application Number: PCT/AU99/00772</p> <p>(22) International Filing Date: 14 September 1999 (14.09.99)</p> <p>(30) Priority Data: PP 5943 15 September 1998 (15.09.98) AU</p> <p>(71) Applicant (for all designated States except US): M.I.M. HOLDINGS LIMITED [AU/AU]; M.I.M. Plaza, 410 Ann Street, Brisbane, QLD 4000 (AU).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): MANLAPIG, Emmanuel, Salvador, Viana [AU/AU]; 8 Tucker Street, Chapel Hill, QLD 4069 (AU). VARGAS, Alfredo, Percy [BO/BO]; Calle 4A, No. 23 Meseta Achumani, La Paz (BO).</p> <p>(74) Agent: BALDWIN SHELSTON WATERS; 60 Margaret Street, Sydney, NSW 2000 (AU).</p>	<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>	

(54) Title: COLLECTORLESS FLOTATION



(57) Abstract

The present invention relates to a process for improving the recovery of valuable sulphide minerals. The process involves determining an Eh range within which the valuable sulphide mineral may be recovered by flotation without the need of a collector. The slurry is then subjected to flotation in a pneumatic cell (50) at such a speed that the slurry remains within the Eh range during flotation. The process substantially reduces or totally eliminates the need for collector. For mixed ores such as chalcopyrite/chalcocite chalcopyrite is recovered without collector, while some non xanthate collector may be required to recover chalcocite.